

reacto CF

Parameter	Norma	MJ	Hodnota							Tolerancia
Plošná hmotnosť	ISO 536	g/m ²	50	57	75	80	90	130	173	± 5 %
Hrúbka	ISO 534	µm	60	67	88	90	107	138	198	± 5
Hladkosť Bekk	ISO 5627	s	90	90	80	80	40	60	40	± 20
Jasnosť R457	ISO 2470	%	93	93	93	93	95	95	95	± 3
Tržná dĺžka pozdĺžne	ISO 1924-1	m	> 5 000							
Absolútna vlhkosť		%	5,8							± 0,3

Popis	Hárok reacto CF predstavuje spodný list sady. Na vrchnej strane má absorbujúci kaolínový náter.
Použitie	Samoprepisovací papier sa používa na vyhotovenie sád formulárov, skladajúcich sa z originálu a jednej alebo viacerých kópií.
Certifikáty	Výrobca je držiteľom certifikátov ISO 9001 – manažment kvality, ISO 14001 – environmentálny manažment, ISO 45001 – bezpečnosť a ochrana zdravia pri práci.
Výrobca	Koehler Paper SE, Nemecko

reacto CF

Property	Standard	Unit	Value							Tolerance
Basis weight	ISO 536	g/m ²	50	57	75	80	90	130	173	± 5 %
Thickness	ISO 534	µm	60	67	88	90	107	138	198	± 5
Smoothness Bekk	ISO 5627	s	90	90	80	80	40	60	40	± 20
Brightness R457	ISO 2470	%	93	93	93	93	95	95	95	± 3
Breaking length MD	ISO 1924-1	m	> 5 000							
Absolute humidity		%	5,8							± 0,3

Description	Reacto CF sheet represents the bottom sheet of a multi-part form. On its front-side is there an absorbent clay coating.
Applications	Carbonless paper is converted into multi-part business forms.
Certificates	The producer holds certificates ISO 9001 – quality, ISO 14001 – environment, ISO 45001 – occupational health and safety.
Producer	Koehler Paper SE, Germany